(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 5 August 2004 (05.08.2004)

PCT

(10) International Publication Number WO 2004/065003 A1

(51) International Patent Classification7: 23/30, C10G 29/20, C07C 7/148, 67/08

B01J 23/28.

(21) International Application Number:

PCT/ZA2004/000007

(22) International Filing Date: 22 January 2004 (22.01.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 2003/0585

22 January 2003 (22.01.2003)

- (71) Applicant (for all designated States except US): SASOL TECHNOLOGY (PTY) LTD [ZA/ZA]; 1 Sturdee Avenue, Rosebank, 2196 Johannesburg (ZA).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW. MX, MZ, NA, NI, NO, NZ, OM, PG. PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM. TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

TECHNOLARY (FIT) LID [AM/A]; 1 Sturee Avenue, Rosebank, 2196 Johannesburg (ZA).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(72) Inventor/Applicant (for US only): BOLDER, Franciscus, Hermanus, Antonius [NLZA]; 25 Leipoldt Street, 1947 Sasoiburg (ZA).

(74) Agents: HAHN, Hans, H. et al.; Hahn & Hahn Inc., 222 Richard Street, Hatfield, 0083 Pretoria (ZA).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidance Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Guidannes Notes on Codes and Abbreviations, refer to the "Gu including contacting the hydrocarbon containing composition with an esterification catalyst at esterfication temperature and pressure. The esterification catalyst includes metal oxides which include one or more oxides selected from molybdenum oxide, tungsten oxide and transition metal oxides in group Ib to VIIIb.



WO 2004/065003

PCT/ZA2004/000007

ESTERIFICATION CATALYST AND PROCESS FOR THE ESTERIFICATION OF ACIDS IN A HYDROCARBONS CONTAINING FEED

Field of the Invention

5

The invention provides an esterification catalyst and an esterification process for the esterification of acids in a hydrocarbons containing feed stream.

Background to the Invention

10

Fischer-Tropsch (FT) product streams are known to contain organic acids, carbonyls, alcohols and other oxygenates, but no sulphur compounds. Removing acids from FT products would allow these products to be hydrogenated at lower temperatures over nickel or other catalyst without introducing sulphur to the process. Removal of acids upstream of the refinery would also reduce the problem of corrosion which is exacerbated by the presence of water in the hydrocarbon streams.

Summary of the Invention

20

25

According to a first aspect of the invention, there is provided an esterification catalyst including one or more catalytically active metal oxides.



The metal oxides may include one or more oxides selected from transition metal oxides in group lb to VIIIb, for example molybdenum oxide or tungsten oxide.

The molybdenum, the tungsten, or the transition metal oxide of the catalyst may be supported on a substrate.

30 The substrate may be alumina, silica-alumina, silica or any other suitable substrate.

According to a second aspect of the invention there is provided an esterification process for the reduction of acids in a hydrocarbon containing composition, said process including contacting the hydrocarbon containing composition with an esterification catalyst at esterification temperature and pressure.

The esterification catalyst may be a catalyst substantially as described above.

The esterification catalyst may be a catalyst selected from the group of transition metal oxides in group lb to VIIIb on alumina substrate, including molybdenum oxide on alumina catalyst and tungsten oxide on alumina catalyst.

The esterification temperature may be from 100°C to 320°C.

15 The esterification temperature may be from 170°C to 250°C.

Typically the esterification temperature is from 190°C to 210°C.

The esterification pressure may be from atmospheric pressure to 100 Bar, typically from 1 to 55 Bar.

The hydrocarbon containing composition may include hydrocarbons of less than 24 carbons i.e. lower than C_{24} .

25 The hydrocarbon containing composition may be a C₄ to C₂₀ hydrocarbons containing composition.

The hydrocarbon containing composition may be a Fischer-Tropsch (FT) condensate fraction.

By FT condensate fraction is meant a condensate fraction of the Fischer-Tropsch reaction products. The condensate fraction is typically obtained as the light stream or overhead stream from a separator after a Fischer-Tropsch reactor in which the Fischer-Tropsch reaction has taken place. Table A below provides typical data for the FT condensate stream.

Table A: Typical Fischer-Tropsch product after separation into two fractions

(vol% distilled)

	FT Condensate (< 270°C fraction)	FT Wax (> 270°C fraction)
C ₅ -160°C	44	3 ·
160-270°C	43	4
270-370°C	13	25
370-500°C		40
> 500°C		28

10

5

The hydrocarbon condensate fraction may be a distilled fraction from the FT condensate fraction. An example of such distilled fraction is shown in table B.

Table B

Carbon number	Mass %
< C ₁₃	1,4
C ₁₃	43,8
C ₁₄	47,2
> C ₁₄	7,6

The hydrocarbon containing composition may have an acid level of 0.5 mg KOH/g or higher.

Typically, the acid level in the hydrocarbon containing composition may be as high as 12 mg KOH/g.

The alcohol to acid ratio in the FT hydrocarbon may be between 9 and 92 on a molar basis.

Methanol or another alcohol may be added to the FT hydrocarbon feed to increase the alcohol to acid ratio.

The product of the process may have an acid level of less than or equal to 0.5 mg KOH/g, generally from 0.1 mg KOH/g to 0.3 mg KOH/g.

The process may be carried out in a continuous flow reactor, like a trickle bed or a flooded bed reactor. The process may also be carried out in a batch reactor.

The process may be carried out at an LHSV of from 0.1 to 5 h⁻¹.

The process may be carried out at an LHSV of from 0.5 and 2 h⁻¹.

Examples of Performing the Invention

15

20

The examples that follow are not intended to limit the scope of the invention and are by way of illustration of the invention only.

Catalysts and operating procedures

A commercial molybdenum on alumina catalyst from BASF (M8-30) was used for experiments 1 to 5. The catalyst is produced in 5 mm diameter extrudates. The

extrudates were crushed and sieved between 0,5 and 2,83 mm and diluted 1:1 with carborundum (0,5-2mm).

Table 1 catalyst composition

5

MoO₃/Al₂O₃ BASFTM M8-30

component	Na2O	MoO3	A1203	Total	
Mass %	0.07	15.61	83.87	100.00	

The catalyst was dried in situ in a hydrogen flow at 125°C and pretreated with hydrogen either at 470°C for 10 hours or at 250°C for 5 hours or heated to operating temperature. The temperature programmed reduction (TPR) shows a reaction with hydrogen around 430°C.

In experiment 6 an extruded WO₃/Al₂O₃ catalyst containing about 20 % tungsten oxide was used which was ground to a particle size between 0.5 and 1 mm.

The experiments 1 to 4 were carried in a 27,5 mm ID bench scale reactor with a total length of 1,5 meter. Bed temperatures were measured with 6 thermocouples axially spaced inside a 6mm OD thermocouple sheath. The reactor was operated in the down flow mode, at 55 bar, 0.56 to 1.5 I/(lcat.h) liquid hourly space velocity (LHSV) and between 385 and 500 $I_n/(lcat.h)$ hydrogen GHSV.

Experiments 5 and 6 were carried out in microreactor with an internal diameter of 12 mm. Bed temperatures were measured with 2 thermocouples axially spaced inside a 3 mm OD thermocouple sheath. The reactor was operated in the down flow mode at 5 bar and 0.56 to 0.67 l/(lcat.h) liquid hourly space velocity (LHSV) and between 300 and 450 l_n/(lcat.h) hydrogen GHSV.

Examples

25

Example 1

The feed in the first experiment consisted of a C₄-C₂₀ Fischer-Tropsch product cut. The hydrocarbon product was passed through a caustic wash which reduced the acids to about 0,5 mg KOH/g. The molar ratio of alcohols to acids in the hydrocarbon feed was 92.

The catalyst was pretreated in hydrogen at 470°C.

10 The results are shown in table 3 below

Table 3

catalyst 1: treated	at 470°C				
T	°C	250	210	190	210
LHSV	h-1	1.5	1.5	1.5	1.5
feed					
ratio alcohol/acid		92	92	92	16.5
acid	mgKOH/g	0.38	0.38	0.38	2.33
carbonyl	mass% as MEK	0.32	0.32	0.32	0.11
alcohol	mass% as C7	6.96	6.96	6.96	7.74
ester	mgKOH/g	0.82	0.82	0.82	0.68
olefins	g Br/100g	47.8	na	47.8	42.9
product					
acid	mgKOH/g	0.01	0.01	0.01	0.02
carbonyl	mass% as MEK	0	0.022	0.09	0.18
alcohol	mass% as C7	0	0.64	6.47	6
ester	mgKOH/g	0	1.2	1.53	2.97
olefins	g Br/100g	80.8	na	45.8	40.8
acids conversion	%	97.37	97.37	97.37	99.14

15 Fresh MoO_x/Al₂O₃ catalyst showed initially considerable catalytic activity towards both esterification and dehydrogenation/dehydration reactions. At the beginning of the run all oxygenates were removed at 250°C and the olefins concentration doubled from 40 to 80 gBr/100g. The latter reactions were however short lived. The residual acids in the effluent stream was 0,01 mg KOH/g.

In the same experiment, in the temperature range of 190 to 210°C, the acids still reacted nearly completely to esters but less of the other oxygenates reacted and over time side reactions decreased.

5

At the lower temperatue the olefinity of the effluent was similar to the value of the feed.

Example 2

10

In this example the feed consisted of C_4 to C_{20} paraffin with a higher acid level (2,3 mg KOH/g). The alcohol concentration was the same as in the previous feed, about 7 mass% as C_7 alcohol. The molar ratio of alcohol to acid of this feed was 16,5.

15

The catalyst treatment was the same as in example 1.

The results are shown in table 3 above.

20

The residual acids in the effluent were between 0,02 and 0,03 mgKOH/g at 210°C. When the temperature was increased to 250°C (after about 5 days), the residual acid level increased to 0.15 mg KOH/g. This may be ascribed to a decrease of the alcohol concentration due to secondary reactions. As a result the alcohol to acid ratio decreased causing a decrease in the conversion to esters.

25

After 3 weeks on line the oxygenates could no longer be removed at a temperature of 250°C. The temperature had to be increased to 310°C before the bulk of the oxygenates was removed.

30 Example 3

In this experiment the molybdenum oxide on alumina catalyst was pretreated in hydrogen at 250°C.

The feed for this experiment was a light condensate fraction derived from low-temperature Fischer-Tropsch synthesis (mainly in the naphtha and diesel range with a small fraction waxy material suspended in it). The acids varied between 1,9 and 2,5 mg KOH/g.

The results are shown in table 4 below

10

At a temperature of 210°C, 1 h⁻¹ LHSV and an alcohol to acid ratio of 14 the conversion of the acids was 98.8 % resulting in an acid number of 0.03 mg KOH/g in the effluent. The same results were obtained at 1,5 h⁻¹ LHSV, which indicated that the reaction was close to equilibrium.

15

The stability of the catalyst was tested at 220°C for 13 days at 1 h⁻¹ LHSV with a different feed (alcohol to acid ratio of 19). The residual acids were 0.05 mgKOH/g and remained stable for as long as these conditions were maintained.

20 At temperatures between 250 and 290°C the acid content of the product increased and only at 310°C did they decrease. Significantly, the olefinity of the product did not increase at these temperatures.



Table 4

5

catalyst 2: treate	d at 250°C		· · · · · · · · · · · · · · · · · · ·					
T	°C	210	210	220	230	250	290	740
LHSV	h-1	1	1.5	1	1	1.5	1.5	310
feed		1		<u>-</u>	-	1.3	1.5	1.5
ratio alcohol/acid		14	14	19	19	14	14	14
acid	mgKOH/g	2.5	2.5	1.9	1.9	2.5	2.5	2.5
carbonyl	mass% as MEK	0.46	0.46	0.4	0.4	0.46	0.46	0.46
alcohol	mass% as C7	7	7	7.4	7.4	7	7	7
ester	mgKOH/g	0.75	0.75	0.97	0.97	0.75	0.75	0.75
olefins	g Br/100g	66.6	- 66.6	68.3	68.3	66.6	66.6	66.6
product							00.0	00.0
acid	mgKOH/g	0.03	0.03	0.05	0.09	0.19	0.6	0.03
carbonyl	mass% as MEK	0.26	0.31	0.21	0.21	0.24	0.29	0.08
alcohol	mass% as C7	6.3	7.2	3.6	3.4	3	0.68	0.18
ester	mgKOH/g	3.2	3.4	2.6	2.6	3.3	0.59	0.05
olefins	g Br/100g	65.0	65.0	71.2	63.2	64.2	67.7	66.0
conversion				1				30.0
acids conversion	%	98.80	98.80	97.37	95.26	92.40	76.00	98.80

Carbonyls were only partly removed and the temperature made little difference to the conversion.

Depending on the temperature, alcohols and carbonyls may react to form a range of compounds and a change in the alcohol to acid ratio will shift the equilibrium from ester to free acids.

- 10 Apart from esterification, alcohols can undergo a variety of other reactions:
 - aldol condensation with aldehydes
 - acetal and ether formation
 - dehydration to olefins
- There was insufficient evidence to conclude that alcohols were dehydrated to olefins because the olefin level did not increase consistently. Temperatures of well above 300°C are required to dehydrate significant amounts of ethanol and propanol to the corresponding olefins.

Example 4

The feed in this experiment consisted of a C_{10} - C_{13} Fischer Tropsch product cut. The hydrocarbon product was high in acids (about 12,5 mg KOH/g) and contained other oxygenates. Methanol was co-fed with the Fischer-Tropsch product at such ratio that the molar ratio of alcohols to acids in the hydrocarbon feed was equal to 10.

The catalyst was molybdenum oxide on alumina which was pretreated in hydrogen at 250°C.

The results are shown in table 5 below.

Table 5

LHSV	h-1	1	1	0.56	0.56
Pressure	bar	40	40	40	5
Temp)	°C	200	220	220	220
Ethanol	g/kg feed	141	141	141	141
alcohol/acid		23.3	23.3	26.1	26.1
SLO feed					
acid	mgKOH/g	10.5	10.5	10	10
carbonyl	mass% as MEK	2.66	2.66	2.96	2.96
alcohol	mass% as C7	50.5	50.5	53.9	53.9
ester	mgKOH/g	5.3	5.3	3.7	3.7
Product					0.07
acids	mgKOH/g	2	0.75	0.34	0.27
carbonyl	mass% as MEK	2.4	2.14	1.6	1.6
alcohol	mass% as C7	25	22.4	27	27
ester	mgKOH/g	12.9	16.2	15.8	15.8
				 	
acid conversion	%	81.0	92.9	96.6	97.3

SLO: Stabilised Light Oil

Example 5

The catalyst was the same as used in experiment 1, but the reaction was carried out in a microreactor. 20 ml Catalyst with a particle size between 0,5 and 1,0 mm was loaded. The catalyst was heated up in a hydrogen stream to the reaction temperature at which point the feed was introduced. The feed consisted of a C₁₃-C₁₄ FT hydrocarbon product fraction with an acid number of 12,6 mg KOH/g. Methanol was co-fed with the FT hydrocarbon. The ratio of alcohol to acid in the mixture was between 9 and 12 on a molar basis. The reaction was carried out at 0,67 h⁻¹ LHSV (hydrocarbon feed), 190 h⁻¹ hydrogen GHSV and 5 bar g pressure.

A reduction of the acids in the hydrocarbon from 12,6 to 0,3 mg KOH/g was achieved in the temperature range of 210 to 230 °C. This amounts to a conversion of 97,7 % of the acids to esters in a single pass.

Example 6

10

15

20

25

30

The catalyst in this example was tungsten oxide on alumina, containing about 20 mass % WO₃.

The equipment and the experimental conditions were the same as described in example 5.

Similar to the previous example, the catalyst was heated up in a hydrogen stream to reaction temperature and the feed introduced.

The results are shown in table 6. The acid concentration in the hydrocarbon was reduced to 0,3 mg KOH/g at 5 bar g, 210 °C, 0,71 h⁻¹ LHSV and an alcohol/acic ration of 17.

Table 6

					7		
Temp	degC	210	220	230	240	190	210
Pres	barg	5	5	5	5	5	5
H2 flow	%	30	30	30	30	30	30
LHSV		0.67	0.67	0.67	0.67	0.71	0.71
Alc/Acid	mol/mol	8.95	8.95	8.95	8.95	17.33	17.33
FEED							
Acid	mgKOH/g	12.6					
Carbonyl	mass% as CO	1.4					
Alcohol	mass% as C7	3.1					
Ester	mgKOH/g	7.2					
PRODUCT	5			1			
Acid	mgKOH/g	0.34	0.43	0.49	0.68	0.55	0.29
Carbonyl	mass% as CO	0.85	1.1	1.1	1.1	1.2	0.95
Alcohol	mass% as C7	2	1	1.6	1.1	3	3.7
Ester	mgKOH/g	14.6	11.9	12.6	12.1	15	14.4

Claims

1. An esterification catalyst including one or more catalytically active metal oxides.

5

- 2. An esterification catalyst as claimed in claim 1, wherein the metal oxides include one or more oxides selected from transition metals in group lb to VIIIb.
- 3. An esterification catalyst as claimed in claim 1, wherein the metal oxide consists of molybdenum oxide or tungsten oxide.
 - 4. An esterification catalyst as claimed in claims 1 to 3, wherein the molybdenum, the tungsten, or any other transition metal oxide is supported on a substrate.

15

- 5. An esterfication catalyst as claimed in claim 4, wherein the substrate is alumina, silica-alumina, or silica.
- 6. An esterification process for the reduction of acids in a hydrocarbon containing composition, said process including contacting the hydrocarbon containing composition with an esterification catalyst at esterfication temperature and pressure.



25

- 7. An esterification process as claimed in claim 6, wherein the esterification catalyst is a catalyst as claimed in claims 1 to 5.
- An esterification process as claimed in claim 6 or claim 7, wherein the esterification catalyst is a catalyst selected from the group of transition metal oxides in group lb to VIIIb on alumina catalyst, including molybdenum oxide on alumina catalyst and tungsten oxide on alumina catalyst.

9. An esterification process as claimed in any one of claims 6 to 8, wherein the esterification temperature is from 100°C to 320°C.

- 10. An esterification process as claimed in claim 9, wherein the esterification temperature is from 170°C to 250°C.
 - 11. An esterification process as claimed in claim 10, wherein the esterification temperature is from 190°C to 210°C.
- 10 12. An esterification process as claimed in any one of claims 6 to 11, wherein the esterification pressure is from atmospheric pressure to 100 Bar.

- 13 An esterification process as claimed in claim 12, wherein the esterification pressure is from 1 to 55 Bar.
- 14. An esterification process as claimed in any one of claims 6 to 13, wherein the hydrocarbon containing composition includes hydrocarbons of less than 24 carbons i.e. lower than C₂₄.
- 20 15. An esterification process as claimed in any one of claims 6 to 13, wherein the hydrocarbon containing composition is a C₄ to C₂₀ hydrocarbons containing composition.
- 16. An esterification process as claimed in any one of claims 6 to 15, wherein25 the hydrocarbon containing composition is a Fischer-Tropsch (FT) condensate fraction.
 - 17. An esterification process as claimed in claim 16, wherein the hydrocarbon condensate fraction is a distilled fraction from the FT condensate fraction.

18. An esterification process as claimed in any one of claims 6 to 17, wherein the hydrocarbon containing composition has an acid level of 0.5 mg KOH/g or higher.

5 19. An esterification process as claimed in claim 18, wherein the acid level in the hydrocarbon containing composition is up to 12 mg KOH/g.

Ŀ

10

15

- 20. An esterification process as claimed in any one of claims 16 to 19, wherein the alcohol to acid ratio in the FT hydrocarbon is between 9 and 92 on a molar basis.
 - 21. An esterification process as claimed in any one of claims 16 to 20, wherein methanol or another alcohol is added to the FT hydrocarbon feed to increase the alcohol to acid ratio.
- 22. An esterification process as claimed in any one of claims 6 to 21, wherein the product of the process has an acid level of less than or equal to 0.5 mg KOH/g.
- 20 23. An esterification process as claimed in any one of claims 6 to 22, wherein the product of the process has an acid level of from 0.1 mg KOH/g to 0.3 mg KOH/g.
 - 24. An esterification process as claimed in any one of claims 6 to 23, wherein the process is carried out in a continuous flow reactor.
 - 25. An esterification process as claimed in any one of claims 6 to 23, wherein the process is carried out at an LHSV of from 0.1 to 5 h⁻¹.
- 26. An esterification process as claimed in any one of claims 6 to 25, wherein the process is carried out at an LHSV of from 0.5 to 2 h⁻¹.

INTERNATIONAL SEARCH REPORT

tni al Application No PCT/ZA2004/000007

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 B01J23/28 B01J23/30

C10G29/20

C07C7/148

C07C67/08

According to International Patent Classification (IPC) or to both national classification and IPC

Minimum documentation searched (classification system followed by classification symbols) IPC 7-801J-C106-C07C

B01J C10G C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, COMPENDEX

C. DOCUMENTS CONSIDERED	TO BE RELEVANT
-------------------------	----------------

	Calegory •	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Alle	X	US 4 415 480 A (MURRELL LAWRENCE L ET AL) 15 November 1983 (1983-11-15) claim 1 examples 1,2; table 1	1–5
	X	US 4 560 797 A (ARMOR JOHN N ET AL) 24 December 1985 (1985-12-24) example 1; tables 1,3	1-5
	X	EP 0 319 065 A (SHELL INT RESEARCH) 7 June 1989 (1989-06-07) examples 1,2	1-5
	X	US 3 846 288 A (CHUN S ET AL) 5 November 1974 (1974-11-05) the whole document	1,2, 4-14,18, 19,22-26
, ave		-/	

l v i	Further documents are listed in the	continuation of hov C

Patent family members are listed in annex.

- . Special categories of cited documents :
- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- document published prior to the international filing date but later than the priority date claimed
- T later document published after the international fiting date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of mailing of the international search report

Date of the actual completion of the international search

2 June 2004

09/06/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo ni, Fax: (+31-70) 340-3016

Authorized officer

Zuurdeeg, B

Form PCT/ISA/210 (second sheet) (January 2004)

INTERNATIONAL SEARCH REPORT

Inte and Application No
PCT/ZA2004/000007

	- CONVENTE CONCINCATO OF SELECTION	
C.(Continua Category *	ation) DOCUMENTS CONSIDERED TO BE RELEVANT Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 968 149 A (MORESCHINI LUCIANO ET AL)	1–5
	6 July 1976 (1976-07-06) the whole document	
A	DE 100 12 163 A (LINDE AG) 20 September 2001 (2001-09-20)	
A	WO 98/25876 A (SASOL CHEMICALS EUROP LTD; VERMAAK ESTER JOHANNA (ZA); JAGER GEERT GU) 18 June 1998 (1998-06-18)	

INTERNATIONAL SEARCH REPORT

Information on patent family members

PCT/ZA2004/00007

				1017 ZAZ	.0047 000007
Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 4415480	Α	15-1:1-1983	NONE		
US 4560797	Α	24-12-1985	US	4624939 A	25-11-1986
EP 0319065	Α	07-06-1989	BR	8805979 A	08-08-1989
			CA	1331376 C	09-08-1994
			CN	1033246 A ,B	07-06-1989
			DE	3867446 D1	13-02-1992
			EP	0319065 A1	07-06-1989
			JP	1164441 A	28-06-1989
			JP	2905488 B2	14-06-1999
			US	4916102 A	10-04-1990
			US 	4940827 A	10-07-1990
US 3846288	Α	05-11-1974	NONE		
US 3968149	Α	06-07-1976	IT	1008392 B	10-11-1976
			BE	826434 A1	08-09-1975
			DE	2509729 A1	11-09-1975
			ES	435338 A1	01-12-1976
			FR	2263222 A1	03-10-1975
			GB	1489834 A	26-10-1977
			JP	50123618 A	29-09-1975
			NL	7502517 A	09-09-1975
DE 10012163	~ A	20-09-2001	DE	10012163 A1	20-09-2001
			ZA	200101977 A	28-11-2001
WO 9825876	Α	18-06-1998	AT	215926 T	15-04-2002
			AU	721229 B2	29-06-2000
			AU	7846698 A	03-07-1998
			BR	9713575 A	14-03-2000
			CA	2274751 A1	18-06-1998
			DE	69711918 D1	16-05-2002
			DE	69711918 T2	22-08-2002
			EP	0944572 A1	29-09-1999
			WO	9825876 A1	18-06-1998
			ID	22495 A	21-10-1999
			TW	474913 B	01-02-2002 09-06-1999
			ZA	9711058 A	